

BS EN 10305-4:2016



BSI Standards Publication

# Steel tubes for precision applications — Technical delivery conditions

Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of EN 10305-4:2016. It supersedes BS EN 10305-4:2011 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/110, Steel Tubes, and Iron and Steel Fittings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 90488 2

ICS 77.140.75

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2016.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

EUROPEAN STANDARD

**EN 10305-4**

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2016

ICS 77.140.75

Supersedes EN 10305-4:2011

English Version

## Steel tubes for precision applications - Technical delivery conditions - Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems

Tubes de précision en acier - Conditions techniques de livraison - Partie 4 : Tubes sans soudure étirés à froid pour circuits hydrauliques et pneumatiques

Präzisionsstahlrohre - Technische Lieferbedingungen - Teil 4: Nahtlose kaltgezogene Rohre für Hydraulik- und Pneumatik-Druckleitungen

This European Standard was approved by CEN on 18 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	6
4 Symbols.....	7
5 Classification and designation.....	7
5.1 Classification.....	7
5.2 Designation.....	7
6 Information to be supplied by the purchaser.....	7
6.1 Mandatory information.....	7
6.2 Options.....	7
6.3 Example of an order.....	8
7 Manufacturing process.....	8
7.1 Steelmaking process.....	8
7.2 Tube manufacture and delivery conditions.....	8
8 Requirements.....	9
8.1 General.....	9
8.2 Chemical composition.....	9
8.3 Mechanical properties.....	10
8.4 Appearance and soundness.....	10
8.5 Dimensions and tolerances.....	11
8.5.1 Outside diameter, inside diameter, wall thickness and eccentricity.....	11
8.5.2 Lengths.....	11
8.5.3 Straightness.....	15
8.5.4 Preparation of ends.....	15
9 Inspection.....	15
9.1 Type of inspection.....	15
9.2 Inspection documents.....	15
9.2.1 Type of inspection documents.....	15
9.2.2 Content of inspection documents.....	15
9.3 Summary of inspection and testing.....	16
10 Sampling.....	17
10.1 Test unit.....	17
10.2 Preparation of samples and test pieces.....	17
10.2.1 General.....	17
10.2.2 Test pieces for the tensile test.....	17
10.2.3 Test pieces for drift expanding test.....	17
10.2.4 Test pieces for roughness measurement.....	17
11 Test methods.....	17
11.1 Tensile test.....	17
11.2 Drift expanding test.....	17

<b>11.3</b>	<b>Dimensional inspection.....</b>	<b>18</b>
<b>11.4</b>	<b>Roughness measurement .....</b>	<b>18</b>
<b>11.5</b>	<b>Visual examination .....</b>	<b>18</b>
<b>11.6</b>	<b>Non-destructive testing .....</b>	<b>18</b>
<b>11.6.1</b>	<b>Testing on longitudinal imperfections.....</b>	<b>18</b>
<b>11.6.2</b>	<b>Leak tightness test.....</b>	<b>18</b>
<b>11.7</b>	<b>Retests, sorting and reprocessing.....</b>	<b>18</b>
<b>12</b>	<b>Marking .....</b>	<b>18</b>
<b>13</b>	<b>Protection and packaging.....</b>	<b>19</b>
<b>13.1</b>	<b>Protection.....</b>	<b>19</b>
<b>13.2</b>	<b>Packaging.....</b>	<b>19</b>
<b>Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of Directive 2014/68/EU aimed to be covered.....</b>		<b>20</b>
<b>Bibliography .....</b>		<b>21</b>



## European foreword

This document (EN 10305-4:2016) has been prepared by Technical Committee ECISS/TC 110 "Steel tubes and iron and steel fittings", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016 and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10305-4:2011.

In comparison with the previous edition, the following technical changes have been made:

- a) References were adapted;
- b) The options were renumbered in such a way that now throughout all parts the number of options are the same;
- c) Precision tubes will now be preferably ordered according to outer diameter and wall thickness;
- d) The drift expanding test is now beside the tensile test the second test for the verification of the mechanical properties;
- e) Editorial updates.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Directive 2014/68/EU.

For relationship with Directive 2014/68/EU, see informative Annex ZA, which is an integral part of this document.

EN 10305, Steel tubes for precision applications - Technical delivery conditions consists of the following parts:

- *Part 1: Seamless cold drawn tubes;*
- *Part 2: Welded cold drawn tubes;*
- *Part 3: Welded cold sized tubes;*
- *Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems;*
- *Part 5: Welded cold sized square and rectangular tubes;*
- *Part 6: Welded cold drawn tubes for hydraulic and pneumatic power systems.*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard specifies the technical delivery conditions for seamless cold drawn steel tubes of circular cross section used in hydraulic and pneumatic power systems.

Tubes according to this document are characterized by having precisely defined tolerances on dimensions and a specified maximum surface roughness.

The allowed pressure rates and upper temperatures are the responsibility of the customer in accordance with the state of the art and in application of the safety coefficients specified in the applicable regulations, codes or standards. Concerning the lower temperature range applicability the impact energy requirements are given at 0 °C.

NOTE Once this standard is published in the Official Journal of the European Union (OJEU) under Directive 2014/68/EU, presumption of conformity to the Essential Safety Requirements (ESRs) of Directive 2014/68/EU is limited to technical data of materials in this standard and does not presume adequacy of the material to a specific item of equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of the Pressure Equipment Directive are satisfied, needs to be done.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10052:1993, *Vocabulary of heat treatment terms for ferrous products*

EN 10168:2004, *Steel products - Inspection documents - List of information and description*

EN 10204:2004, *Metallic products - Types of inspection documents*

EN 10266:2003, *Steel tubes, fittings and structural hollow sections - Symbols and definitions of terms for use in product standards*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 2566-1, *Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 4287, *Geometrical product specifications (GPS) - Surface texture: Profile method - Terms, definitions and surface texture parameters (ISO 4287)*

EN ISO 6892-1:2016, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 8492, *Metallic materials - Tube - Flattening test (ISO 8492)*

EN ISO 8493:2004, *Metallic materials - Tube - Drift-expanding test (ISO 8493:1998)*

EN ISO 10893-1:2011, *Non-destructive testing of steel tubes - Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness (ISO 10893-1:2011)*

EN ISO 10893-2, *Non-destructive testing of steel tubes - Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)*

EN ISO 10893-3, *Non-destructive testing of steel tubes - Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3)*

EN ISO 10893-10, *Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*

ISO 11484:2009, *Steel products - Employer's qualification system for non-destructive testing (NDT) personnel*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020:2000, EN 10021:2006, EN 10052:1993, EN 10266:2003 and the following apply.

#### 3.1

##### **employer**

organization for which a person works on a regular basis

Note 1 to entry: The employer can be either the tube manufacturer or a third party organization providing services, such as non-destructive testing (NDT).

#### 3.2

##### **manufacturer**

party to produce and to deliver tubes in accordance with this document

Note 1 to entry: Where tubes are delivered by an intermediary, see EN 10021:2006, Clause 6.

#### 3.3

##### **imperfection**

discontinuity in the wall or on the pipe surfaces detectable by methods described in this document

Note 1 to entry: Imperfections with a size complying with the acceptance criteria specified in this document are considered to have no practical implication on the intended use of the product.

#### 3.4

##### **defect**

imperfection of a size not complying with the acceptance criteria specified in this document

Note 1 to entry: Defects are considered to adversely affect or limit the intended use of the product.



### 3.5

#### **mother tube**

length of tube produced in the final cold drawing process

## 4 Symbols

For the purposes of this document, the symbols in EN 10266:2003 apply.

## 5 Classification and designation

### 5.1 Classification

In accordance with the classification system in EN 10020:2000, the steel grades given in Table 1 are non-alloy quality steels.

### 5.2 Designation

For the tubes covered by this document, the steel designation consists of the number of this document (EN 10305-4) plus either:

- a) the steel name in accordance with EN 10027-1; or
- b) the steel number in accordance with EN 10027-2.

## 6 Information to be supplied by the purchaser

### 6.1 Mandatory information

The following information shall be obtained by the manufacturer at the time of enquiry and order:

- a) quantity (mass or total length or number);
- b) term "tube";
- c) dimensions, preferably by outside diameter  $D$  and wall thickness  $T$  (or other pair of dimensions), (see 8.5.1.1 and Table 4);
- d) steel designation (see 5.2);
- e) type of tube length (see 8.5.2);
- f) type of inspection certificate (see 9.1).

### 6.2 Options

A number of options are specified in this document and these are listed below. In the event that the purchaser does not indicate his wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 6.1).

- Option 4: Surface condition for further processing (see 8.4.1);
- Option 7: Reduced internal roughness of  $\leq 2 \mu\text{m}$  (see 8.4.2);

- Option 8: Measurement of surface roughness (see 8.4.3);
- Option 12: Non-destructive testing for the detection of longitudinal imperfections (see 8.4.6);
- Option 21: another specified length and/or tolerance (see 8.5.2);
- Option 22: Reduced maximum deviation from straightness (see 8.5.3);
- Option 28: Alternative marking (see Clause 12);
- Option 31: Protection by phosphatization (see 13.1);
- Option 33: Protection by galvanization and chromatization, type blue-white (see 13.1);
- Option 34: Protection by galvanization and chromatization, type yellow (see 13.1);
- Option 35: Protection by galvanization and chromatization, type olive green (see 13.1);
- Option 36: Protection by galvanization and passivation (type Cr (VI) free) (see 13.1);
- Option 37: Protection of tube ends (see 13.1);
- Option 38: Unbundled tubes or specific method of packaging (see 13.2).

### 6.3 Example of an order

1 000 m tubes with an outside diameter of  $D = 20$  mm and a wall thickness of  $T = 2,5$  mm in accordance with this document, made of steel grade E235, delivered in standard lengths, protected by phosphatization and with an inspection certificate 3.1 in accordance with EN 10204:2004:

1 000 m tubes –  $D 20 \times T 2,5$  – EN 10305-4 – E235 – standard length – option 31 – inspection certificate 3.1

## 7 Manufacturing process

### 7.1 Steelmaking process

The steel making process is at the discretion of the manufacturer with the exception that the open hearth (Siemens-Martin) process shall not be employed unless in combination with a secondary steelmaking or ladle refining process.

Steels shall be fully killed.

NOTE This excludes the use of rimming, balanced or semi-killed steel.

### 7.2 Tube manufacture and delivery conditions

**7.2.1** The tubes shall be manufactured from hot finished seamless hollows by cold drawing.

The tubes shall be delivered in the delivery condition +N which means that after the final cold drawing operation the tubes are normalized in a controlled atmosphere.

**7.2.2** All non-destructive testing (NDT) activities shall be carried out by qualified and competent level 1, 2 and/or 3 personnel authorized to operate by the employer.

The qualification shall be in accordance with ISO 11484:2009 or, at least, an equivalent to it.

It is recommended that the level 3 personnel be certified in accordance with EN ISO 9712 or, at least, an equivalent to it.

The operating authorization issued by the employer shall be in accordance with a written procedure. NDT operations shall be authorized by a level 3 NDT individual approved by the employer.

NOTE The definition of level 1, 2 and 3 can be found in appropriate standards, e.g. EN ISO 9712 and ISO 11484:2009.

## 8 Requirements

### 8.1 General

The tubes, when inspected in accordance with Clauses 9, 10, and 11, shall comply with the requirements of this document.

In addition, the general technical delivery requirements specified in EN 10021 apply.

### 8.2 Chemical composition

The cast analysis reported by the steel producer shall apply and comply with the requirements of Table 1.

NOTE When subsequently welding tubes produced in accordance with this document, it is important to take account of the fact that the behaviour of the steel during and after welding is dependent not only on the steel composition and the delivery condition but also on the conditions of preparing for and carrying out the welding.

**Table 1 — Chemical composition (cast analysis)**

Steel grade		% by mass					
Steel name	Steel number	C max.	Si max.	Mn max.	P max.	S max.	Al <sub>tot</sub> <sup>a</sup> min.
E215	1.0212	0,10	0,05	0,70	0,025	0,015	0,025
E235	1.0308	0,17	0,35	1,20	0,025	0,015	0,015
E355	1.0580	0,22	0,55	1,60	0,025	0,015	0,020
Elements not quoted in this table (but see footnote a) shall not be intentionally added to the steel without the agreement of the purchaser, except for elements which may be added for the purposes of deoxidation and/or nitrogen binding. All appropriate measures shall be taken to prevent the addition of undesirable elements from scrap or other materials used in the steel making process.							
<sup>a</sup> This requirement is not applicable provided the steel contains a sufficient amount of other nitrogen binding elements, such as Ti, Nb or V. If added, the content of these elements shall be reported in the inspection document. When using titanium, the manufacturer shall verify that $(Al + Ti/2) \geq 0,020$ .							

Table 2 specifies the permissible deviations of product analysis from the specified limits on cast analysis given in Table 1.

**Table 2 — Permissible deviations of the product analysis from the specified limits on the cast analysis given in Table 1**

Element	Specified limit of the cast analysis % by mass	Permissible deviation of the product analysis % by mass
C	≤ 0,22	+ 0,02
Si	≤ 0,55	+ 0,05
Mn	≤ 1,60	+ 0,10
P	≤ 0,025	+ 0,005
S	≤ 0,015	+ 0,003
Al	≥ 0,015	- 0,005

### 8.3 Mechanical properties

The mechanical properties of the tubes shall conform to the requirements of Table 3 and 11.2.

**Table 3 — Mechanical properties at room temperature**

Steel grade		Yield strength <sup>a</sup>	Tensile strength	Elongation after fracture
Steel name	Steel number	$R_{eH}$ min. MPa	$R_m$ MPa	$A$ min. %
E215	1.0212	215	290 to 430	30
E235	1.0308	235	340 to 480	25
E355	1.0580	355	490 to 630	22
The steel grades defined in this document have an intrinsic minimum transverse impact energy of 27 J at 0 °C.				
<sup>a</sup> For tubes with outside diameter $D \leq 30$ mm and wall thickness $T \leq 3$ mm, the $R_{eH}$ minimum values are 10 MPa lower than the values given in this table.				

### 8.4 Appearance and soundness

**8.4.1** The internal and external surface finish of the tubes shall be typical of the manufacturing process and, where applicable, the heat treatment employed.

**Option 4:** A surface condition suitable for special further processing is specified by the purchaser.

Normally, the finish and surface condition shall be such that any surface imperfections requiring dressing can be identified. Any surface imperfections, which in accordance with the manufacturer's experience might be considered defects as specified in 8.4.4, shall be dressed in accordance with 8.4.5, or the tube or part of tube shall be rejected.

**8.4.2** The tubes shall have smooth outer and inner surfaces with a roughness  $R_a \leq 4$   $\mu\text{m}$ , unless option 7 is specified.

NOTE In the case of the inner surface, this requirement applies to inside diameters  $\geq 15$  mm.

**Option 7:** *A roughness of  $Ra \leq 2 \mu\text{m}$  is specified for the inner surface.*

**8.4.3** Verification of surface roughness and/or improved levels of roughness may be specified (see option 8).

**Option 8:** *The surface roughness shall be measured in accordance with 11.4 and reported.*

**8.4.4** Surface imperfections which encroach on the specified minimum wall thickness shall be considered defects and tubes containing these shall be deemed not to conform to this document.

**8.4.5** It shall be permissible to dress, only by grinding or machining, surface imperfections provided that, after doing so, the wall thickness in the dressed area is not less than the specified minimum wall thickness. All dressed areas shall blend smoothly into the contour of the tube.

**8.4.6** Non-destructive testing for the detection of longitudinal imperfections may be specified (see option 12).

**Option 12:** *Non-destructive testing of the full tube circumference for the detection of longitudinal imperfections in accordance with 11.6.1 is specified.*

**8.4.7** For verification of leak-tightness, the tubes shall pass a non-destructive test in accordance with 11.6.2.

## 8.5 Dimensions and tolerances

### 8.5.1 Outside diameter, inside diameter, wall thickness and eccentricity

**8.5.1.1** The tubes shall be supplied preferably by outside diameter  $D$  and wall thickness  $T$  (or by outside diameter  $D$  and inside diameter  $d$  or inside diameter  $d$  and wall thickness  $T$ ).

**8.5.1.2** Preferred outside diameters with tolerances, inside diameters with tolerances and wall thicknesses with tolerances are given in Table 4.

Depending on the ordered pair of dimensions (see 8.5.1.1) either the tolerances on specified outside diameter and specified wall thickness or on specified outside diameter and specified inside diameter or on specified inside diameter and specified wall thickness apply.

Dimensions which are different from those in Table 4 may be agreed at the time of enquiry and order. In this case, the tolerances and surface roughness shall also be agreed.

The diameter tolerances include the out-of-roundness. For a maximum distance of 100 mm, the ends may, due to the cutting method, have diameters outside the tolerances.

**8.5.1.3** For tubes specified by the outside and the inside diameter, the eccentricity shall fulfil the following requirement:

$$\frac{T_{\max} - T_{\min}}{T_{\max} + T_{\min}} \times 100 \leq 10 \% \quad (1)$$

where

$T_{\max}$  and  $T_{\min}$  are measured in the same cross section.

### 8.5.2 Lengths

The type of tube lengths shall be specified at the time of enquiry and order by either:



— a standard length of 6 m  $\begin{smallmatrix} +50 \\ 0 \end{smallmatrix}$  mm or

— an exact length of 6 m  $\begin{smallmatrix} +10 \\ 0 \end{smallmatrix}$  mm ,

unless option 21 is specified.

5 % of shorter lengths may be supplied provided they are not shorter than 4 m and bundled separately.

**Option 21:** Another length and/or tolerance is specified.

**Table 4 — Sizes and tolerances**

Dimensions in millimetres

Specified outside diameter $D$ with tolerance <sup>a</sup>		Specified inside diameter $d$ with tolerance <sup>a</sup>		Specified wall thickness $T$ with tolerance <sup>a</sup>	
4	$\pm 0,08$	3	$\pm 0,15$	0,5	$\pm 0,10$
		2		1	$\pm 0,10$
5	$\pm 0,08$	3,5	$\pm 0,15$	0,75	$\pm 0,10$
		3		1	$\pm 0,10$
6	$\pm 0,08$	4	$\pm 0,12$	1	$\pm 0,10$
		3	$\pm 0,15$	1,5	$\pm 0,15$
		2		2	$\pm 0,20$
8	$\pm 0,08$	6	$\pm 0,10$	1	$\pm 0,10$
		5		1,5	$\pm 0,15$
		4	$\pm 0,15$	2	$\pm 0,20$
		3		2,5	$\pm 0,25$
10	$\pm 0,08$	8	$\pm 0,08$	1	$\pm 0,10$
		7	$\pm 0,12$	1,5	$\pm 0,15$
		6	$\pm 0,15$	2	$\pm 0,20$
		5		2,5	$\pm 0,25$
12	$\pm 0,08$	10	$\pm 0,08$	1	$\pm 0,10$
		9	$\pm 0,10$	1,5	$\pm 0,15$
		8	$\pm 0,12$	2	$\pm 0,20$
		7	$\pm 0,15$	2,5	$\pm 0,25$
		6		3	$\pm 0,30$
14	$\pm 0,08$	12	$\pm 0,08$	1	$\pm 0,10$
		11		1,5	$\pm 0,15$
		10	$\pm 0,10$	2	$\pm 0,20$
		9	$\pm 0,12$	2,5	$\pm 0,25$
		8	$\pm 0,15$	3	$\pm 0,30$
15	$\pm 0,08$	13	$\pm 0,08$	1	$\pm 0,10$
		12		1,5	$\pm 0,15$
		11	$\pm 0,10$	2	$\pm 0,20$
		10	$\pm 0,12$	2,5	$\pm 0,25$
		9	$\pm 0,15$	3	$\pm 0,30$

Specified outside diameter $D$ with tolerance <sup>a</sup>		Specified inside diameter $d$ with tolerance <sup>a</sup>		Specified wall thickness $T$ with tolerance <sup>a</sup>	
16	$\pm 0,08$	14	$\pm 0,08$	1	$\pm 0,10$
		13		1,5	$\pm 0,15$
		12	$\pm 0,10$	2	$\pm 0,20$
		11	$\pm 0,12$	2,5	$\pm 0,25$
		10	$\pm 0,15$	3	$\pm 0,30$
18	$\pm 0,08$	16	$\pm 0,08$	1	$\pm 0,10$
		15		1,5	$\pm 0,15$
		14		2	$\pm 0,20$
		13	$\pm 0,15$	2,5	$\pm 0,25$
		12		3	$\pm 0,30$
20	$\pm 0,08$	17	$\pm 0,08$	1,5	$\pm 0,15$
		16	$\pm 0,15$	2	$\pm 0,20$
		15		2,5	$\pm 0,25$
		14		3	$\pm 0,30$
		13		3,5	$\pm 0,35$
		12	4	$\pm 0,40$	
22	$\pm 0,08$	20	$\pm 0,08$	1	$\pm 0,10$
		19		1,5	$\pm 0,15$
		18		2	$\pm 0,20$
		17		2,5	$\pm 0,25$
		16	$\pm 0,15$	3	$\pm 0,30$
		15		3,5	$\pm 0,35$
		14		4	$\pm 0,40$
25	$\pm 0,08$	22	$\pm 0,08$	1,5	$\pm 0,15$
		21		2	$\pm 0,20$
		20		2,5	$\pm 0,25$
		19	$\pm 0,15$	3	$\pm 0,30$
		17		4	$\pm 0,40$
		16		4,5	$\pm 0,45$
		15		5	$\pm 0,50$
28	$\pm 0,08$	25	$\pm 0,08$	1,5	$\pm 0,15$
		24		2	$\pm 0,20$
		23		2,5	$\pm 0,25$
		22	$\pm 0,15$	3	$\pm 0,30$
		20		4	$\pm 0,40$
		18		5	$\pm 0,50$
30	$\pm 0,08$	26	$\pm 0,08$	2	$\pm 0,20$
		25		2,5	$\pm 0,25$
		24	$\pm 0,15$	3	$\pm 0,30$
		22		4	$\pm 0,40$
		20		5	$\pm 0,50$
		18		6	$\pm 0,60$

Specified outside diameter $D$ with tolerance <sup>a</sup>		Specified inside diameter $d$ with tolerance <sup>a</sup>		Specified wall thickness $T$ with tolerance <sup>a</sup>	
35	±0,15	31	±0,15	2	±0,20
		30		2,5	±0,25
		29		3	±0,30
		27		4	±0,40
		25		5	±0,50
		23		6	±0,60
38	±0,15	34	±0,15	2	±0,20
		33		2,5	±0,25
		32		3	±0,30
		30		4	±0,40
		28		5	±0,50
		26		6	±0,60
		24		7	±0,70
		22		8	±0,80
42	±0,20	38	±0,20	2	±0,20
		36		3	±0,30
		34		4	±0,40
		32		5	±0,50
		30		6	±0,60
		26		8	±0,80
50	±0,20	42	±0,20	4	±0,40
		40		5	±0,50
		38		6	±0,60
		34		8	±0,80
		32		9	±0,90
		30		10	±1,00
55	±0,25	47	±0,25	4	±0,40
		43		6	±0,60
		39		8	±0,80
		35		10	±1,00
60	±0,25	50	±0,25	5	±0,50
		44		8	±0,80
		40		10	±1,00
		35		12,5	±1,25
70	±0,30	60	±0,30	5	±0,50
		54		8	±0,80
		50		10	±1,00
		45		12,5	±1,25
80	±0,35	68	±0,35	6	±0,60
		64		8	±0,80
		60		10	±1,00
		55		12,5	±1,25

<sup>a</sup> Dimensions and tolerances only apply for the ordered pair of dimensions (see 8.5.1.1 and 8.5.1.2).

### 8.5.3 Straightness

For tubes with an outside diameter  $D > 15$  mm supplied in lengths greater than 1 000 mm, the deviation from straightness of any tube length  $L$  shall not exceed  $0,0015 L$ . Deviations from straightness over any one metre length shall not exceed 3 mm, unless option 22 is specified.

**Option 22:** *A reduced maximum deviation from straightness is specified.*

### 8.5.4 Preparation of ends

The tubes shall be delivered with square cut ends. The ends shall be free from harmful burrs.

NOTE For outside diameters  $D < 8$  mm or inside diameters  $d < 4$  mm, the tubes may have deformed ends.

## 9 Inspection

### 9.1 Type of inspection

Products complying with this document shall be ordered and delivered with one of the inspection documents as specified in EN 10204. The type of document shall be agreed upon at the time of enquiry and order. If the order does not contain any specification of this type, inspection certificate 3.1 shall be issued.

### 9.2 Inspection documents

#### 9.2.1 Type of inspection documents

In the case of non-specific inspection a test report 2.2 in accordance with EN 10204:2004 shall be issued.

When specific inspection is requested, an inspection certificate 3.1 or 3.2 in accordance with EN 10204:2004 shall be issued. If an inspection certificate 3.2 is ordered the purchaser shall additionally notify the manufacturer of the name and address of the organization or person who is to carry out the inspection and produce the inspection document. It shall also be agreed which party shall issue the certificate.

#### 9.2.2 Content of inspection documents

**9.2.2.1** The content of the inspection document shall be in accordance with EN 10168:2004 as shown in 9.2.2.2 and 9.2.2.3.

**9.2.2.2** For tubes supplied with non-specific inspection, the test report 2.2 shall contain the following codes and information:

A	commercial transactions and parties involved;
B	description of products to which the inspection applies;
C10 to C13	tensile test;
C60 to C69	other tests;
C71 to C92	chemical composition;
D01	marking, surface appearance, shape and dimensional properties;
D02 to D99	leak tightness test;
Z	validation.

**9.2.2.3** For tubes supplied with specific inspection the inspection certificate 3.1 or 3.2 shall contain the following codes and information:

A	commercial transactions and parties involved;
B	description of products to which the inspection document applies;
C10 to C13	tensile test;
C60 to C69	other tests;
C71 to C92	chemical composition (cast analysis);
D01	marking, surface appearance, shape and dimensional properties;
D02 to D99	leak tightness test and other (optional) tests (e.g. roughness measurement, NDT on longitudinal imperfections);
Z	validation.

### 9.3 Summary of inspection and testing

Inspection and testing shall be carried out as stated in Table 5 and 10.1.

**Table 5 — Summary of inspection and testing**

Type of inspection or test		Frequency of testing <sup>a</sup>		Reference
		Non-specific inspection	Specific inspection	
mandatory	Chemical analysis	M	M	8.2
	Tensile test	M	one per test unit	8.3, 11.1
	Drift expanding test <sup>b</sup>	M	2 per test unit	11.2
	Dimensional inspection	M	M	8.5, 11.3
	Visual examination	M	M	11.5
	NDT for verification of leak tightness	Each individual tube	Each individual tube	8.4.7, 11.6.2
optional	Roughness measurement (option 8)	not applicable	one per test unit	8.4.3, 11.4
	NDT on longitudinal imperfections (Option 12)	not applicable	Each individual tube	8.4.6, 11.6.1

<sup>a</sup> M : according to manufacturer's procedure.

<sup>b</sup> For tubes with outside diameters  $D > 150$  mm and/or wall thicknesses  $T > 10$  mm, instead of the drift expanding test the flattening test may be applied (see Table 6).



## 10 Sampling

### 10.1 Test unit

A test unit is defined as a quantity of tubes of the same steel grade and dimensions, the same cast, manufactured by the same process and heat treated in the same batch and the same heat treatment facility.

NOTE In the case of a continuous heat treatment furnace, a batch is the lot heat treated without intermission with the same process parameters.

A test unit shall comprise not more than 500 mother tubes with a maximum of 10 000 m.

### 10.2 Preparation of samples and test pieces

#### 10.2.1 General

Samples and test pieces shall be taken at the tube ends and in accordance with EN ISO 377 from one sample tube per test unit.

#### 10.2.2 Test pieces for the tensile test

The test pieces shall be prepared in accordance with EN ISO 6892-1:2016.

#### 10.2.3 Test pieces for drift expanding test

The test pieces for the drift expanding test shall consist of a full tube section, in accordance with EN ISO 8493:2004.

#### 10.2.4 Test pieces for roughness measurement

The test pieces should be taken from the same location as for the mechanical tests.

## 11 Test methods

### 11.1 Tensile test

The test shall be carried out at room temperature in accordance with EN ISO 6892-1:2016 and the following determined:

- the tensile strength  $R_m$ ;
- the upper yield strength  $R_{eH}$ ;

If a yield phenomenon is not present the 0,2 % proof strength  $R_{p0,2}$  shall be determined;

- the percentage elongation  $A$  after fracture with a reference to a gauge length  $L_0$  of  $5,65\sqrt{S_0}$  ;

If a non-proportional test piece is used, the percentage elongation value shall be converted to the value for a gauge length  $L_0 = 5,65\sqrt{S_0}$  using the conversion tables given in EN ISO 2566-1.

### 11.2 Drift expanding test

The test shall be carried out in accordance with EN ISO 8493:2004 with a 60° conical mandrel. The tube section shall be expanded until the increase in diameter reaches the applicable values shown in Table 6.

**Table 6 — Requirements for the drift expanding test**

Steel grade		% increase of the diameter <i>D</i> for	
Name	Number	<i>T</i> ≤ 4 mm	<i>T</i> > 4 mm
E215	1.0212	20	15
E235	1.0308	18	12
E355	1.0580	15	10

For outside diameters above 150 mm and/or wall thicknesses above 10 mm, instead of the drift expanding test the flattening test may be applied as described in EN ISO 8492 (see also EN 10305-1, 11.2).

After testing, the test piece shall be free from cracks or breaks. However, a slight cracking at the edges shall not be considered cause for rejection.

### 11.3 Dimensional inspection

Specified dimensions, including straightness, shall be verified. Diameter measurements shall be carried out at a distance of ≥ 100 mm from the tube ends (see 8.5.1.2).

### 11.4 Roughness measurement

Roughness shall be measured in the axial direction in accordance with EN ISO 4287.

### 11.5 Visual examination

Tubes shall be visually examined for compliance with the requirements of 8.4.1 and 8.5.3.

### 11.6 Non-destructive testing

#### 11.6.1 Testing on longitudinal imperfections

Non-destructive testing for the detection of longitudinal imperfections shall be carried out, at the discretion of the manufacturer, in accordance with one or more of the following methods:

- a) eddy current testing: EN ISO 10893-2, acceptance level E3;
- b) magnetic transducer/flux leakage testing: EN ISO 10893-3, acceptance level F3;
- c) ultrasonic testing: EN ISO 10893-10, acceptance level U3B.

#### 11.6.2 Leak tightness test

Non-destructive testing for verification of leak-tightness shall be carried out in accordance with EN ISO 10893-1:2011.

### 11.7 Retests, sorting and reprocessing

For retests, sorting and reprocessing EN 10021 applies.

## 12 Marking

Unless option 28 is specified, the following marking shall be applied indelibly on each tube. The marking shall be repeated continuously along a line parallel to the tube axis, with a maximum interval of 1,5 m between two sequences, 5 % of the tubes may contain only one mark.

When one of the options 33 to 36 is specified, marking may be applied on a label attached to the bundle or the box.

The marking shall include the following information:

- the manufacturer's name or trade mark;
- the specified dimensions;
- the number of this European Standard;
- the steel name;
- in the case of specific inspection, an identification number (e.g. order or item number) which permits the correlation of the product or delivery unit to the related document.

**Option 28:** *An agreed alternative marking is specified.*

## 13 Protection and packaging

### 13.1 Protection

The tubes shall be delivered with a temporary protection against corrosion. The type of protection shall be at the discretion of the manufacturer, unless otherwise specified (see options 31, 33 to 37). The manufacturer shall take appropriate measures to prevent ingress of foreign matter into the tube.

**Option 31:** *The tubes shall be phosphatized before temporary protection.*

**Option 33:** *The external surface of the tubes shall be galvanized and chromated type blue-white. The zinc thickness shall be specified by the purchaser.*

**Option 34:** *The external surface of the tubes shall be galvanized and chromated type yellow. The zinc thickness shall be specified by the purchaser in accordance with an appropriate specification.*

**Option 35:** *The external surface of the tubes shall be galvanized and chromated type olive. The zinc thickness shall be specified by the purchaser.*

**Option 36:** *The external surface of the tubes shall be galvanized and passivated (type Cr (VI) free).*

**Option 37:** *The tube ends shall be protected with plugs or caps.*

### 13.2 Packaging

The tubes shall be delivered bundled, with polygonal bundles for tubes of  $\geq 12$  mm outside diameter, unless option 38 is specified.

**Option 38:** *Supply of unbundled tubes or application of a specific packaging method is specified.*

## Annex ZA (informative)

### Relationship between this European Standard and the Essential Requirements of Directive 2014/68/EU aimed to be covered

This European Standard has been prepared under a Commission's standardization request M/071 to provide one voluntary means of conforming to essential requirements of Directive 2014/68/EU.

Once this standard is cited in the Official Journal of the European Union under that Directive, compliance with the normative clauses of this standard given in Table ZA.1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding essential requirements of that Directive and associated EFTA regulations.

**Table ZA.1 — Correspondence between this European Standard and Annex I of the Directive 2014/68/EU**

Essential Requirements of the Directive 2014/68/EU	Clauses/sub-clauses of this EN	Remarks/ Notes
4.1a	8.3	Appropriate material properties
4.1c	8.2	Ageing
4.1d	7.2.1, 8.4	Suitable for the processing procedures
4.3	Clause 9	Inspection documentation  NOTE: Details about the materials certification of the various pressure-bearing parts may be found in the PED EC Guideline 7/5.  A test report for non specific product control does only comply with main pressure-bearing parts of pressure equipment in category I.  An inspection certificate 3.1 or 3.2 for specific product control is required for the main pressure-bearing parts of pressure equipment in categories II, III and IV.

**WARNING 1** — Presumption of conformity stays valid only as long as a reference to this European Standard is maintained in the list published in the Official Journal of the European Union. Users of this standard should consult frequently the latest list published in the Official Journal of the European Union.

**WARNING 2** — Other Union legislation may be applicable to the product(s) falling within the scope of this standard.

## Bibliography

- [1] EN ISO 9712, *Non-destructive testing - Qualification and certification of NDT personnel (ISO 9712)*
- [2] Directive 2014/68/EU of the European Parliament and of the Council of 15 May 2014 on the harmonisation of the laws of the Member States relating to the making available on the market of pressure equipment
- [3] PED-guideline 7/5 "Pressure equipment directive 97/23/EC. Commission's Working Group 'Pressure'. Guideline related to: Annex I Section 4.3"









# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK